



American Institute of Timber Construction

7012 South Revere Parkway • Suite 140 • Centennial, CO 80112

Phone: 303/792-9559 Fax: 303/792-0669

AITC 117-2004

STANDARD SPECIFICATIONS FOR STRUCTURAL GLUED LAMINATED TIMBER OF SOFTWOOD SPECIES ANNEX C

-and-

AITC GRADING HANDBOOK FOR LAMINATING LUMBER – 2004

ERRATA

June, 2004

Subsequent to their printing, errors were discovered in some of the labeling of laminating grades included in Annex C of AITC 117-2004, and in the AITC Grading Handbook for Laminating Grades – 2004.

The following addition to Section 4.2.2.1 is hereby adopted:

- *Exception:* “L1” for Douglas Fir-Larch/Douglas Fir South is considered dense. No density designation as per 4.2.2 is required.

Also, the following section is hereby adopted:

4.2.2.1.a L1

- Density: Medium (except Douglas Fir-Larch/Douglas Fir South, which is dense).
- Knot Size: Knots shall not occupy more than 1/4 of the cross-section.
- Slope of Grain: The basic slope of grain shall not exceed 1:14 for the full length of the piece.

References to “L1D” for DF/L in Table 8.2, and Table B1 of AITC 117 are hereby changed to “L1”.